## G10 Arctic Blue Nitrile Gloves

## Product Information

|       |      | Palm Width* | Glove Length* |                               |  |
|-------|------|-------------|---------------|-------------------------------|--|
| Code  | Size | Unit: (mm)  | Unit: (mm)    | Quantity                      |  |
| 90095 | XS   | 70          | 242           | 200 Gloves/Box. 10 Boxes/Case |  |
| 90096 | S    | 80          | 242           | 200 Gloves/Box. 10 Boxes/Case |  |
| 90097 | Μ    | 95          | 242           | 200 Gloves/Box. 10 Boxes/Case |  |
| 90098 | L    | 110         | 242           | 200 Gloves/Box. 10 Boxes/Case |  |
| 90099 | XL   | 120         | 242           | 200 Gloves/Box. 10 Boxes/Case |  |
|       |      |             |               |                               |  |

\*As measured by ASTM D 6319; ASTM D 3578; 2.5 AQL<sup>1</sup>

| Property                    | Description  |
|-----------------------------|--|
| General Product Information | Category I PPE (CE Simple) according to the PPE Directive (89/686/EEC)   |
| General Description         | Arctic blue nitrile, powder free, non-sterile, textured fingertip, ambidextrous gloves, beaded cuff, online chlorinated on donning side, powder free coagulant on the grip side. Not made with natural rubber latex. |

| Physical Property     | Unit     | Upper Limit | Test Method |
|-----------------------|----------|-------------|-------------|
| Residual Powder Level | mg/glove | 1           | ASTM D 6124 |

| Thickness     | Target   | Test Method (2.5 AQL)            |
|---------------|----------|----------------------------------|
| Middle Finger | 0.078 mm | ASTM D 6319; ASTM 3767; EN 455-2 |
| Palm          | 0.058 mm | ASTM D 6319; ASTM 3767; EN 455-2 |
| Cuff          | 0.046 mm | ASTM D 6319; ASTM 3767; EN 455-2 |

| Property                           | Tensile Strength | Test Method (2.5 AQL) |
|------------------------------------|------------------|-----------------------|
| Tensile Strength - Before Aging    | 21 Mpa           | ASTM D 412            |
| Tensile Strength - After Aging     | 28 Mpa           | ASTM D 573            |
|                                    |                  | ASTM D 3578           |
| Ultimate Elongation – Before Aging | 600%             | ASTM D 412            |
| Ultimate Elongation – After Aging  | 550%             | ASTM D 573            |
| - • •                              |                  | ASTM D 3578           |

<sup>1</sup> AQL levels defined according to ISO 2859-1 (current edition) Sampling Procedures for Inspection by Attributes.

<u>Workmanship Requirement</u>: Gloves shall be made in accordance with reasonable industry practice with respect to defects, dirt and contamination. Gloves should be packaged as specified having described size and color in the appropriate quantity as listed. Shipping Case and inner packaging shall be labeled with product name, size, lot / batch and catalog number.

For Additional information: Contact your Kimberly-Clark representative, our Customer Service Team (888)-346-GOKC (4652) or KCPInfo@kcc.com

Rev. 10/2017

Kimberly-Clark warrants that its products (1) comply with K-C's standard specifications as of the delivery date to K-C's authorized distributors/direct purchasers and are warrantied for the following periods from end user's date of purchase (verified by valid sales receipt) (a) five years for Balder Technology auto darkening filters; (b) two years for all other auto darkening filters; and (c) one year for powered air purlying respirators; (2) comply with all K-C labeling representations; and (3) are manufactured in compliance with all applicable federal, state, and local laws in effect at the time and place of manufacture of the products. THIS WARRANTY IS IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. K-C is not liable for any kind of special, incidental, or consequential damages. K-C's liability for breach of contract, tort or other cause of action shall not exceed the product purchase price. Purchasers and users are deemed to have accepted the above warranty and limitation of liability, and cannot change the terms by verbal agreement or by any writing not signed by K-C. To the extent required by applicable law, K-C does not limit its liability for death/injury resulting from K-C's negligence.

